## **Duct Liner Adhesive**

### Detail

Premium grade water based duct liner adhesive.

- Water Based
- Color: Black or White
- UL Classified
- Chemical Type: Synthetic Latex
- Fast Dry Time
- Exceptional Coverage: 400 sq.ft./gal
- Apply by Brush, Spray or Roto Bond
- Water Resistant
- Dry Time: 11 minutes at 76°F, depending on temperature, humidity and application thickness
- Initial Tack: Exceptional wet tack with smooth finish after drying ASTM D6195 Standard Test Methods for Loop Tack: 0.32 oz./in. Optimum Tack @ 4-5 minutes of drying (>1.6 oz./in.)
- Density: 9.1 ± 0.2 lbs/gallon
- Solids: 46 ± 2%
- Viscosity: 4,000 cps ± 2,000 cps (Brookfield Viscosmeter, RV-3 spindle, 5 rmps, at 77°F)
- Application Temp: 20°F to 90°F
- Storage Temp: 20°F to 90°F
- Non-flammable in wet and dry states
- Shelf Life: (Unopened containers) 1 year
- Meets ASTM C 916 Type II
- Meets NFPA 90A & 90B
- LEED 4v Compliant
- TVOC Emissions: CDPH Standard Method v1.2 = Private Office - Pass: School Classroom - Pass
- VOC Content: EPA Method 24 Test = Pass Very Low
- Contains antimicrobials and fungicides to prevent mold growth
- Easily sprayed with airless or spray assisted sprayers (see spray chart for recommended spray equipment)
- Can wipe clean with soapy water when wet. Stronger solvents will be needed if dried.
- Do not freeze

### Packaging

Item	Description	Packaging	Weight
DLADHESIVE5B	Duct Liner Adhesive - Black 5 gal pail	Each	46 lbs/pail
DLADHESIVE54B	Duct Liner Adhesive - Black 54 gal drum	Each	555 lbs/drum
DLADHESIVE5W	Duct Liner Adhesive - White 5 gal pail	Each	46 lbs/pail
DLADHESIVE54W	Duct Liner Adhesive - White 54 gal drum	Each	555 lbs/drum





c U us

File No. R15765 SURFACE BURNING CHARACTERISTICS

> Applied to Inorganic Reinforced Cement Board+

"FHC 25/50" + - Tested as applied in two 2 in. wide strips 8 in. on center covering 22.2% of the test sample area at a coverage rate of 400 sq. ft. per gallon.

> SURFACE BURNING CHARACTERISTICS IN ACCORDANCE WITH CAN/ULC-S102

Applied to Inorganic Reinforced Cement Board++

"FHC 25/50" ++ - Tested applied in two 50mm wide strips 200mm on center covering 22.2% of the test sample area at a coverage rate of 9.8 m²/L.



# **SMACNA**

### CONTACT

Office: 888.973.7600

1100 Ashwood Drive Suite 1102 Canonsburg, PA 15317 Can

#### www.clward.com