## **S-Seal Spray**

## **Detail**

## Premium grade water based duct sealant

- Indoor and outdoor use
- UL 723 Classification
- UL 181B-M Listed
- Conforms to requirements of NFPA 90A and 90B
- Manufactured by SMART Local #12
- Extremely Flexible ASTM D522 (1/8" Madrel Bend) Pass
- For applications up to 15" w.g.
- Base: Synthetic latex
- · Color: Gray
- Density: 11±.2 lbs per gallonSolid Contents: 62% ±2%
- Viscosity: 80,000 ±20,000 cps (Brookfield Viscometer, HB-5 spindle, 5 rpms, at 77°F)
- Application Temp: 35°F to 100°F
- Adhesion Strength per UL 181B Peel Adhesion Pass, overeds standards
- exceeds standards
- Service Temp: -25°F to 220°FStorage Temp: 35°F to 110°F
- Dry To Touch: 1 hour (approx.)
- Cure Time: 24 to 72 hours + (depending on humidity,
  - application, and temperature)
- Mold Resistance: UL 181B Mold & Humidity Test Pass
- Water Resistance: Excellent
  Freeze Thaw Stability: Pass
  Coverage: 25 sq.ft./gal. at 1/16" 50 sq.ft./gal. at 1/32"
- Odor: Mild (wet) None (dry)
- Shelf Life: 1 year (unopened)
- Cured Sealant: Tough and permanently flexible
- Ultraviolet Ray and Ozone resistent
- LEED Compliant, meets all applicable SCAQMD standards
- VOC Content: EPA Method 24 Test = Pass Very Low
- TVOC Emissions: CDPH Standard Method v1.2 = Private Office - Pass; School Classroom - Pass







USC - Classification
Applied to Introgenic Reinforced Cement Board ±
PHC 25/00
ted as applied in two 2 in, wide strips spaced 8 in, on center covering 22.2% of the exposed temple area at a coverage rate of 25 fiviliation.

FHC 25/50
 FHC 25/50



## **Packaging**

Item	Description	Packaging	Weight
SSEALSPRAY5	S-Seal Spray 5 gal	each	64 lbs/pail

44





**CONTACT** 

Office: 888.973.7600

1100 Ashwood Drive Suite 1102 Canonsburg, PA 15317

www.clward.com